


**GREAT LAKES
GRANITE & MARBLE**



12275 Dixie

Telephone: (313) 362-0123

E-mail: info@greatlakesgm.com

Redford, MI 48239

Fax (313) 531-1585

Home Page: www.greatlakesgm.com

APPLICATION OF SEALER ON STONE

TESTING: Always test each surface before overall application to ensure suitability and desired results.

DIRECTIONS: Surfaces to be treated must be clean and free of loose debris, dirt, mildew, oils and grease. Adjacent areas that may be sensitive to solvents should be protected. The surface should be air-dry and absorbent. Sealer may be applied by brushing, sponging or low pressure spraying to saturation. Allow up to 15 minutes to dry for penetration. Wipe the surface area clean and apply a second application. Ten to 20 minutes after the second application or before surface drying, remove all excess material from the surface. To avoid buildup of surface film, we recommend rubbing the newly treated surface with "000" steel wool or a clean, dry rag. No material should remain on the surface. Allow 24 hours for full cure.

CAUTION: Chemical product. Flammable. Contains petroleum distillates. Use adequate ventilation. Protect adjacent materials. Avoid eye and skin contact. If exposed, wash and flush with water. Keep out of the reach of children.

Approximate coverage is 600 to 800 square feet per gallon for polished surfaces. However, coverage may vary depending upon porosity of the substrate.